

Bleached Liner

Regular Hold Out

Regular Hold Out Bleached Liner is excellent for applications where the highest levels of print gloss are not required. It provides high brightness and good hold out, and is printable by most printers.

	42
Grade Code	BW42RH
Conditioned Basis Wt (7.5%H₂O), lbs/1000sf <i>Tappi T 410</i> Nominal Reject Below	42 40.0
Moisture Average, % <i>Tappi T 412</i> Average (%) Range (+ / -)	7.0 -1.2 / +1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5
Porosity (Gurley), sec/100cc <i>Tappi T 460</i> Reject Below	20
Cobb 30 Minute (TOP), g/m² <i>Tappi T 441</i> Reject Above	155
Smoothness, Sheffield Units <i>Tappi T 538</i> Sheffield – Range (Typical)	100
Brightness, % <i>ISO 2469 & 2470</i> Average (%) Range (+ / -)	80 2
Caliper, mils <i>Tappi T 411</i> Average Typical CD Roll Variability	9.8 + / - 1