

## Coated White Top Liner

### Light

Coated White Top Liner is designed to offer ultimate flexibility for high graphics users. This grade offers the ability to generate high print gloss and ink density, along with superior runnability and convertibility.

	29	31	33
<b>Grade Code</b>	CW287LT	CW31LT	CW33LT
<b>Conditioned Basis Wt (7.5%H<sub>2</sub>O), lbs/1000sf</b>			
Tappi T 410			
Nominal	28.7	31	33
Reject Above	30.2	32.5	34.5
Reject Below	27.2	29.5	31.5
<b>Moisture Average, %</b>			
Tappi T 412			
Average (%)	6.6	6.6	6.6
Range (+ / -)	-1.1 / +1.5	-1.1 / +1.5	-1.1 / +1.5
<b>Moisture Variation, %</b>			
Maximum 2-Sigma (CD)	1.5	1.5	1.5
<b>Ring Crush (CD), lbr</b>			
Tappi T 822			
Reject Below	--	--	--
<b>STFI (CD), lbr/in</b>			
Tappi T 826			
Reject Below	--	12.9	14.6
<b>Porosity (Gurley), sec/100cc</b>			
Tappi T 460			
Reject Below	20	20	20
<b>Cobb 30 Minute (TOP), g/m<sup>2</sup></b>			
Tappi T 441			
Reject Above	155	155	155
<b>Smoothness, PPS</b>			
Tappi T 555			
Typical	3.0	3.0	2.8
Reject Above	3.3	3.3	3.1
<b>Brightness, %</b>			
ISO 2469 & 2470			
Average (%)	80	80	80
Range (+ / -)	2	2	2
<b>Caliper, mils</b>			
Tappi T 411			
Average	5.5	5.9	6.7
Typical CD Roll Variability	+ / - 1	+ / - 1	+ / - 1