

Coated White Top Liner

Light

Coated White Top Liner is designed to offer ultimate flexibility for high graphics users. This grade offers the ability to generate high print gloss and ink density, along with superior runnability and convertibility.

	33	37	41	46
Grade Code	CW33LT	CW37LT	CW41LT	CW46LT
Conditioned Basis Wt (7.5%H₂O), lbs/1000sf <i>Tappi T 410</i>				
Nominal	33	37	41	46
Reject Above	34.5	39.0	43.0	48.0
Reject Below	31.5	35.0	39.0	44.0
Moisture Average, % <i>Tappi T 412</i>				
Average (%)	6.6	6.6	6.6	6.6
Range (+ / -)	-1.1 / +1.5	-1.1 / +1.5	-1.1 / +1.5	-1.1 / +1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5	1.5	1.5	1.5
Ring Crush (CD), lbr <i>Tappi T 822</i>				
Reject Below	--	--	--	80
STFI (CD), lbr/in <i>Tappi T 826</i>				
Reject Below	14.6	16.4	18.4	--
Porosity (Gurley), sec/100cc <i>Tappi T 460</i>				
Reject Below	20	20	20	20
Cobb 30 Minute (TOP), g/m² <i>Tappi T 441</i>				
Reject Above	155	155	155	155
Smoothness, PPS <i>Tappi T 555</i>				
Typical	2.8	2.8	2.8	3.0
Reject Above	3.1	3.1	3.1	3.3
Brightness, % <i>ISO 2469 & 2470</i>				
Average (%)	80	80	80	80
Range (+ / -)	2	2	2	2
Caliper, mils <i>Tappi T 411</i>				
Average	6.7	7.7	8.1	8.8
Typical CD Roll Variability	+ / - 1	+ / - 1	+ / - 1	+ / - 1