

Kraft Liner

Kraft Liner combines excellent strength and printability characteristics.

	26	30	33	38
Grade Code	KL26	KL30	KL33	KL38
Conditioned Basis Wt (7.5%H_2O), lbs/1000sf <i>Tappi T 410</i>				
Nominal	26	30	33	38
Reject Below	25.0	29.0	32.0	36.5
Moisture Average, % <i>Tappi T 412</i>				
Average (%)	Mill Specific	Mill Specific	Mill Specific	Mill Specific
Range (+ / -)	1.5	1.5	1.5	1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5	1.5	1.5	1.5
Mullen, psi <i>Tappi T 807</i>				
Reject Below	60	60	72	84
Ring Crush (CD), lbr <i>Tappi T 822</i>				
Reject Below	--	--	--	--
STFI (CD), lbr/in <i>Tappi T 826</i>				
Reject Below	11.4	13.2	14.6	16.4
Porosity (Gurley), sec/100cc <i>Tappi T 460</i>				
Reject Below	10	10	10	12
Internal Bond, ft-lb/in² <i>Tappi T 569</i>				
Scott Bond - Reject Below	75	75	75	75
Slide Angle (Degrees) <i>Tappi T 815</i>				
Reject Below	18	18	18	18
Cobb 2 Minute (TOP), g/m² <i>Tappi T 441</i>				
Reject Below	30	30	30	30
Reject Above	60	60	60	60
Cobb 30 Minute (TOP), g/m² <i>Tappi T 441</i>				
Reject Above	155	155	155	155
Wax Pick <i>Tappi T 459</i>				
Reject Below	16	16	16	16
Smoothness, Sheffield units <i>Tappi T 538</i>				
Sheffield - Range (Typical)	350/390	350/390	350/390	350/390
Caliper, mils <i>Tappi T 411</i>				
Average	Mill Specific	Mill Specific	Mill Specific	Mill Specific
Typical CD Roll Variability	+ /- 1	+ /- 1	+ /- 1	+ /- 1