

Kraft Liner

High Performance

High Performance Kraft Liner provides the same print characteristics as our regular Kraft Liner, but offers additional resistance to crushing.

	35	46	52	56	62	72
Grade Code	KL35HP	KL46HP	KL52HP	KL56HP	KL62HP	KL72HP
Ring Crush (CD), lbr <i>Tappi T 822</i> Reject Below	--	90	102	115	133	150
STFI (CD), lbr/in <i>Tappi T 826</i> Reject Below	18.4	--	--	--	--	--
Moisture Content, % <i>Tappi T 412</i> Average (%) Range (+/-)	Mill Specific 1.5	Mill Specific 1.5	Mill Specific 1.5	Mill Specific 1.5	Mill Specific 1.5	Mill Specific 1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5	1.5	1.5	1.5	1.7	2.0
Porosity (Gurley), sec/100cc <i>Tappi T 460</i> Reject Below	12	12	12	12	12	12
Internal Bond, ft-lb/in ² <i>Tappi T 569</i> Scott Bond - Reject Below	75	75	75	75	75	75
Slide Angle (Degrees) <i>Tappi T 815</i> Reject Below	18	18	18	18	18	18
Cobb 2 Minute (TOP), g/m ² <i>Tappi T 441</i> Reject Below Reject Above	30 60	30 60	30 60	30 60	30 60	30 60
Cobb 30 Minute (TOP), g/m ² <i>Tappi T 441</i> Reject Above	155	155	155	155	155	155
Wax Pick Reject Below	16	16	16	16	16	16
Smoothness, Sheffield Units <i>Tappi T 538</i> Sheffield – Reject Above	350/390	350/390	350/390	350/390	350/390	350/390
Caliper, mils <i>Tappi T 411</i> Average Range	Mill Specific +/-1	Mill Specific +/-1	Mill Specific +/-1.5	Mill Specific +/-1.5	Mill Specific +/-1.5	Mill Specific +/-1.5