

Medium

Medium is produced with either 100% recycled fiber or a blend of recycled and virgin (NSSC). All of our medium products offer excellent strength and runnability on the corrugator.

	23	26	30	33
Grade Code	ME23	ME26	ME30	ME33
Conditioned Basis Wt (7.5%H₂O), lbs/1000sf <i>Tappi T 410</i>				
Nominal	23	26	30	33
Reject Below	22.0	25.0	28.5	31.5
Moisture Average, % <i>Tappi T 412</i>				
Average (%)	Mill Specific	Mill Specific	Mill Specific	Mill Specific
Range (+ / -)	1.5	1.5	1.5	1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5	1.5	1.5	1.5
Concora, lb_r <i>Tappi T 809</i>				
Reject Below	50	55	55	55
CFC (CD), lb_r <i>Tappi T 843</i>				
Reject Below	50	55	70	80
Water Absorbency, sec <i>Tappi T 832</i>				
Curl – Aged Mill Test	3/35 sec	3/35 sec	3/35 sec	3/35 sec

Conversion from CFC to Ring Crush: $RC = (CFC \times .78) - 13.3$ for estimation purposes only.

Conversion from Ring Crush to CFC: $CFC = (RC \times 1.28) + 17.0$ for estimation purposes only.