

Medium

Medium is produced with either 100% recycled fiber or a blend of recycled and virgin (NSSC). All of our medium products offer excellent strength and runnability on the corrugator.

	36	40	45
Grade Code	ME36	ME40	ME45
Conditioned Basis Wt (7.5%H₂O), lbs/1000sf <i>Tappi T 410</i>			
Nominal	36	40	45
Reject Below	34.0	38.0	43.0
Moisture Average, % <i>Tappi T 412</i>			
Average (%)	Mill Specific	Mill Specific	Mill Specific
Range (+ / -)	1.5	1.5	1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5	1.5	1.5
Concora, lbr <i>Tappi T 809</i>			
Reject Below	60	60	65
CFC (CD), lbr <i>Tappi T 843</i>			
Reject Below	90	100	115
Water Absorbency, sec <i>Tappi T 832</i>			
Curl – Aged Mill Test	3/35 sec	3/35 sec	3/35 sec

Conversion from CFC to Ring Crush: $RC = (CFC \times .78) - 13.3$ for estimation purposes only.

Conversion from Ring Crush to CFC: $CFC = (RC \times 1.28) + 17.0$ for estimation purposes only.