

Wet Strength Bleached Liner

Regular Hold Out

Wet Strength Bleached Liner provides extra protection in damp or humid conditions, while still providing a clean consistent print surface with high brightness and good ink hold out.

	56
Grade Code	BW56WS
Conditioned Basis Wt (7.5%H ₂ O), lbs/1000sf <i>Tappi T 410</i> Nominal Reject Below	-- --
Moisture Average, % <i>Tappi T 412</i> Average (%) Range (+ / -)	7.0 -1.2 / +1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5
Mullen (Dry), psi <i>Tappi T 807</i> Reject Below	--
Mullen (Wet), psi <i>Tappi T 807</i> Reject Below	39
Ring Crush (CD), lbr <i>Tappi T 822</i> Reject Below	115
Internal Bond, ft-lb/in ² <i>Tappi um 833</i> Scott Bond - Reject Below	75
Porosity (Gurley), sec/100cc <i>Tappi T 460</i> Reject Below	20
Cobb 30 Minute (TOP), g/m ² <i>Tappi T 441</i> Reject Above	155
Smoothness, Sheffield Units <i>Tappi T 538</i> Sheffield – Range (Typical)	100
Brightness, % <i>ISO 2469 & 2470</i> Average (%) Minimum	78 73