

## White Top Liner

White Top Liner has uniform and consistent ink absorption characteristics and provides an excellent visual appearance.

	26	29	31	33
Grade Code	WT26	WT29	WT31	WT33
Conditioned Basis Wt (7.5%H <sub>2</sub> O), lbs/1000sf <i>Tappi T 410</i>				
Nominal	26	29	31	33
Reject Below	25.0	28.0	29.0	32.0
Moisture Average, % <i>Tappi T 412</i>				
Average (%)	Mill Specific	Mill Specific	Mill Specific	Mill Specific
Range (+ / -)	1.5	1.5	1.5	1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5	1.5	1.5	1.5
Mullen, psi <i>Tappi T 807</i>				
Reject Below	60	60	60	72
Ring Crush (CD), lbr <i>Tappi T 822</i>				
Reject Below	--	--	--	--
STFI (CD), lbr/in <i>Tappi T 826</i>				
Reject Below	--	--	12.9	14.6
Porosity (Gurley), sec/100cc <i>Tappi T 460</i>				
Reject Below	15	15	15	15
Internal Bond, ft-lb/in <sup>2</sup> <i>Tappi UM 808</i>				
Peel - Reject Below	0.8	0.8	0.8	0.8
Cobb 30 Minute (TOP), g/m <sup>2</sup> <i>Tappi T 441</i>				
Reject Above	155	155	155	155
Smoothness, Sheffield units <i>Tappi T 538</i>				
Sheffield - Reject Above	265	265	310	310
Brightness, % <i>ISO 2469 &amp; 2470</i>				
Average (%)	72.5	72.5	72.5	72.5
Range (+ / -)	2	2	2	2
Caliper, mils <i>Tappi T 411</i>				
Average	Mill Specific	Mill Specific	Mill Specific	Mill Specific
Typical CD Roll Variability	+ / - 1	+ / - 1	+ / - 1	+ / - 1