

White Top Liner

White Top Liner has uniform and consistent ink absorption characteristics and provides an excellent visual appearance.

	38	42	69
Grade Code	WT38	WT42	WT69
Conditioned Basis Wt (7.5%H₂O), lbs/1000sf <i>Tappi T 410</i>			
Nominal	38	42	69
Reject Below	36.5	40.5	67.0
Moisture Average, % <i>Tappi T 412</i>			
Average (%)	Mill Specific	Mill Specific	Mill Specific
Range (+ / -)	1.5	1.5	1.5
Moisture Variation, % Maximum 2-Sigma (CD)	1.5	1.5	1.7
Mullen, psi <i>Tappi T 807</i>			
Reject Below	84	95	128
Ring Crush (CD), lbr <i>Tappi T 822</i>			
Reject Below	--	--	115
STFI (CD), lbr/in <i>Tappi T 826</i>			
Reject Below	16.4	18.4	--
Porosity (Gurley), sec/100cc <i>Tappi T 460</i>			
Reject Below	15	15	15
Internal Bond, ft-lb/in² <i>Tappi um-808</i>			
Peel - Reject Below	0.8	0.8	0.8
Cobb 30 Minute (TOP), g/m² <i>Tappi T 441</i>			
Reject Above	155	155	155
Smoothness, Sheffield units <i>Tappi T 538</i>			
Sheffield - Reject Above	330	340	380
Brightness, % <i>ISO 2469 & 2470</i>			
Average (%)	72.5	72.5	72.5
Range (+ / -)	2	2	2
Caliper, mils <i>Tappi T 411</i>			
Average	Mill Specific	Mill Specific	Mill Specific
Typical CD Roll Variability	+ / - 1	+ / - 1	+ / - 1.5